

TOTAL PREMIUM-S

SILICONIZED ELASTOMERIC FINISH COAT

888.702.9915
www.totalwall.com

SILICONIZED ELASTOMERIC ACRYLIC FINISH COAT

AMERICA'S EIFS AND STUCCO COMPANY!

Total Premium-S Siliconized Elastomeric Finish is a high quality trowel grade textured coating material with extraordinary stain and dirt resistance. Total Premium-S is pre-colored, pre-textured and ready to trowel on directly out of the pail. The eight standard textures available are:

Shot Blast Coarse- a deep sand blast texture;

Shot Blast Medium- a rich sand blast texture;

Shot Blast Fine- a porous lime stone texture;

Swirl Ultra Coarse- a deep open swirl pattern;

Swirl Coarse- a medium open swirl pattern;

Swirl Fine - a light swirl pattern;

Freestyle - produces a variety of patterns;

Gemstone - a variety of marble-like finishes.



Features

- Elastomeric acrylic coating
- Meets VOC, VOS requirements
- Superior mold & mildew resistance
- Provides a long-lasting finish
- 180% Elongation
- Resists dirt pickup and is non-chalking

Coverage

Texture	Coverage
Shot Blast Fine	140 - 170 sq.ft. / pail
Shot Blast Medium	100 - 120 sq.ft. / pail
Shot Blast Coarse	70 - 100 sq.ft. / pail
Swirl Fine	140 - 160 sq.ft. / pail
Swirl Coarse	130 - 160 sq.ft. / pail
Swirl Ultra Coarse	90 - 120 sq.ft. / pail
Freestyle	80 - 140 sq.ft. / pail
Gemstone	140 - 160 sq.ft. / pail

Total Premium-S provides a weatherproof, attractive egg-shell finish that is designed for a maximum degree of elongation, permanent flexibility, maximum adhesion and long term durability.

All Total Premium-S finishes are formulated with high-grade quality pigments and resins exceed all industry standards for performance and durability. In addition, Total Premium-S Finishes have elongation (180%) capable of handling a high degree of thermal movement and bridging hairline cracks.

Total Premium-S Elastomeric Finishes are suited for all exterior and interior applications.

Application

The substrate must be clean and free of loose particles, oils or any substance that would interfere with bond. A smooth cementitious substrate (such as T2000 or T-Wall Hard Coat Base Coat) is recommended. For interior use, any smooth substrate (such as drywall) will do. A smooth, even substrate will provide better coverage, uniform texture, and a better result than a rough substrate. Glossy surfaces need to be roughened.

Open a new 5-gallon pail of Total Premium-S Elastomeric Finish and mix with a low speed mechanical for 1 minute. If necessary, add up to 6 ounces of clean water to adjust workability. Using a stainless steel trowel, apply Total Premium-S Elastomeric Finish to the substrate. Use firm pressure and trowel to trowel on the coating.

For Swirl textures, trowel to the thickness of the largest aggregate in the Total Premium Elastomeric Finish. For Gemstone, and Shot Blast textures, trowel to a thickness a little greater than the largest aggregate. Try not to over-trowel the coating. Work to

a natural stop or break. Float the finish within 2 - 5 minutes after being troweled, depending on drying conditions. Do not let the Total Premium-S Elastomeric Finish begin to dry before floating is completed.

For the ShotBlast finishes, a plastic float or stainless steel trowel are often used. For the Swirl textures, a foam float or plastic trowel is often used. The face of the trowel or float is kept flat to the wall using light to moderate pressure and circular sweeping strokes. Do not over-float the Finish.

Freestyle texture responds to different floating techniques to produce stipple, skip trowel, knock-down or other attractive textures. The applicator must apply a thin skim coat and then a second coat which the applicator produces the final texture.

Handling and Storage

Do not apply to frozen or saturated surfaces. Do not apply if precipitation is forecast within 8 hours of application. Do not apply if the temperature cannot be maintained above 40F for 24 hours. Shelf life in closed containers is 12-18 months when stored at 50-100F. Keep containers

sealed and under cover when not in use.

Maintenance

If Total Premium-S Elastomeric Finish becomes dirty or stained, clean with a mild cleaner solution and low-pressure spray rinse. For scars or hard to clean stains, recoat with T-Wall Elastomeric.

Precautions

Total Premium-S Elastomeric Finish is an alkaline water based material. Do not ingest. Avoid contact with skin and eyes. In case of contact, flush with water. For contact with eyes, get immediate medical attention in addition to flushing.

Wear safety glasses and protective clothing. Keep out of reach of children and pets.

Technical Data

Technical Data

Flash point	>200 F	Seta
Density	11.5 lb/gal	
Viscosity	approx 1 MM cps	
pH	9.0 - 9.8	
Elongation	180%	ASTM D412
Solids	> 80%	ASTM D1044
Accelerated Weathering	2000 hrs pass	ASTM G23
Mildew Resistance	Pass	Mil Std 810D
Flame Spread Index	5	ASTM E84